

BLANK PAGE



भारतीय मानक

वस्त्रादि — हैवी सी पटसन का कपड़ा — विशिष्टि

(पहला पुनरीक्षण)

Indian Standard

TEXTILES — HEAVY CEE JUTE CLOTH — SPECIFICATION

(First Revision)

UDC 677:13:064

© BIS 1993

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110 002

Jute and Jute Products Sectional Committee, TX 03

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Jute and Jute Products Sectional Committee had been approved by the Textile Division Council.

This standard was first published in 1966. This standard is being revised so as to align it with IS 9113: 1992 regarding general requirements and criteria of conformity.

For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2: 1960 'Rules for rounding off numerical values (revised). The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

TEXTILES — HEAVY CEE JUTE CLOTH — SPECIFICATION

(First Revision)

	1 SCOPE		IS No.	Title
This standard prescribes constructional details and other requirements of heavy cee jute cloth.		9030 : 1979	Method for determination of seam strength of jute fabrics including their laminates	
2 REFERENCES		9113:1992	Textile — Jute sacking —	
The following Indian Standards are necessary adjuncts to this standard:		General requirement (revision)		
IS No. Title		3 TERMINOLOGY		
	1954 : 1990	Methods for determination of length and width of fabrics (second revision)	For the purpose of this standard, the definition given in IS 5476: 1986 shall apply.	
1963: 1981 Method for determination		,	4 GENERAL F	REQUIREMENTS
		threads per unit length in woven	4 4 4 4 4 4 4 4 4 4 4 4 4 4 4 4 4 4 4 4	
	1969:1985	Method for determination of breaking load and elongation of woven textile fabrics (second revision)	and straight selvedges. If agreed to between buyer and the seller there shall be colou stripes woven according to the agreement.	
2387:1969		Method for determination of	4.2 Freedom fr	om Defects
		weight of jute fabrics (first revision)	The cloth should defects, such as	ld be generally free from weaving holes, cuts, tears, floats, crushed
	2873: 1991	73: 1991 Textile — Packaging of jute products in bales—Specification		s, stains.
		(first revision)	5 SPECIFIC R	EQUIREMENTS
	2969:1974	Method for determination of oil content of jute yarn and fabrics (first revision)	5.1 The cloth s specified in Tal	hall conform to the requirements ole 1.
	5476:1986	Glossary of terms relating to jute (first revision)		ontaining the cloth shall conform nents specified in Table 2.

Table 1 Particulars of Heavy Cee Jute Cloth

(Clause 5.1)

Characteri o	stic Requirement	Tolerance	Method of Test
) Width	71 cm	+4 cm -0 cm	IS 1954:1990
) Mass per square metre	673 g	+67 g 51 g	IS 2387: 1969
Ends per dm	68	±4	IS 1963: 1981
Picks per dm	35	±2	IS 1963: 1981
Average breaking load (revelled strip method,			IS 1969:1985
Warpway	160 kg		
Weftway	180 kg		

NOTE — The buyer and the seller may agree to the width other than specified above. In that case, tolerance of $\begin{array}{c} +4 \\ -0 \end{array}$ cm shall apply,

Table 2 Requirements of Packed Bales

(Clause 5.2)

SI No.	Characteristic	Requirement	Method of Test
i)	Total length of fabric per bale	As declared or specified	IS 1954: 1990
ii)	Number of medium and short cuts per bale	see elause 5.1.7 of IS 2873: 1991	 .
iii)	Contract mass of a bale	As declared or specified	-
iv)	Corrected net mass of a bale	Not less than contract mass	8.1 of IS 9113:1992
v)	Moisture regain	22 percent, Max	8.2 of IS 9113: 1992
vi)	Oil content on dry deoiled material basis	8·0 percent, Max	IS 2969: 1974

6 PACKING

The cloth shall be packed in bales as prescribed in IS 2873:1991 or as specified in an agreement between the buyer and seller.

7 MARKING

7.1 The bales shall be marked as prescribed in IS 2873: 1991. Additional markings shall be made as stipulated by the buyer or required by the regulation or law in force.

7.2 The bales may also be marked with the Standard Mark.

8 SAMPLING AND CRITERIA FOR CONFORMITY

8.1 The sampling shall be as laid down in IS 9113: 1992.

8.2 The lot shall be considered as conforming to the requirements of this standard if the conditions as laid down in IS 9113: 1992 are satisfied.

AMENDMENT NO. 1 OCTOBER 2005 TO

S 3751:1993 TEXTILES — HEAVY CEE JUTE CLOTH — SPECIFICATION

(First Revision)

[Page 2, Table 2, Sl No. (vi), Under 0'.	'Requirement'] — Substitute '3' for
ΓX 03)	Rencography Unit RIS New Delhi India

Standard Mark

The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the Bureau of Indian Standards Act, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, types or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc: No. TX 03 (0089)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 331 01 31, 331 13 75	Telegrams: Manaksanstha
	(Common to all Office)

	(common to an Omices)
Regional Offices:	Telephone
Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{331 01 31 331 13 75
Eastern: 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola CALCUTTA 700054	{37 84 99, 37 85 61 37 86 26, 37 86 62
Northern: SCO 445-446, Sector 35-C, CHANDIGARH 160036	{53 38 43, 53 16 40 53 23 84
Southern: C. I. T. Campus, IV Cross Road, MADRAS 600113	{235 02 16, 235 04 42 {235 15 19, 235 23 15
Western: Manakalaya, E9 MIDC, Marol, Andheri (East) BOMBAY 400093	{632 92 95, 632 78 58 632 78 91, 632 78 92

Branches: AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. PATNA. THIRUVANANTHAPURAM.